

Material

95 AU V142

blue

revision index

8

revision date

9/27/2019

page

1 / 3

Physical properties

	nominal range	typical values	
Density DIN EN ISO 1183-1, 23 °C	1.20 ±0.02	1.20	g/cm ³
Hardness DIN ISO 7619-1, Shore A, 23 °C	94 ±3	94	Shore
Hardness DIN ISO 7619-1, Shore D, 23 °C	46 ±5	46	Shore
Modulus 100 %, DIN 53504, S2, 23 °C	> 11	13.8	MPa
Modulus 300 %, DIN 53504, S2, 23 °C	---	23	MPa
Tensile strength DIN 53504, S2, 23 °C	> 48	58	MPa
Elongation at break DIN 53504, S2, 23 °C	> 430	540	%
Tear strength DIN ISO 34-1, B (b), 23 °C	---	110	KN/m
Compression set DIN ISO 815, 24 h, 70 °C, 10 %	---	24	%
Compression set DIN ISO 815, 24 h, 100 °C, 10 %	---	29	%
Low Temperature ISO 11357-2, DSC	---	-36	°C
Torsions pendulum test DIN EN ISO 6721-2A	---	-22	°C
Surface resistivity DIN EN 62631-3-1 (VDE 0307-3-1) Ausgabe 2016, 50 %, 23 °C	---	4,1 E +12	Ohm
Durchgangswiderstand 500 V, 23 °C, 50 %	---	> 1,0 E +12	Ohm*cm
Temperature range	-30°C to 110°C		

Declarations of conformity

Freudenberg

Freudenberg FST GmbH
Global Material Technology
Wolfgang Becker
Telefon: +49 (0)6201/80-2893
Fax: +49 (0)6201/88-2893
Email: wolfgang.becker@FST.com

Material
95 AU V142
blue

revision index
8

revision date
9/27/2019

page 2 / 3

RoHS conform

Country Part

Remark

including EU 2011/65 and
EU2015/863 (ROHS III)

Expires unlimited



Freudenberg

Freudenberg FST GmbH
Global Material Technology
Wolfgang Becker
Telefon: +49 (0)6201/80-2893
Fax: +49 (0)6201/88-2893
Email: wolfgang.becker@FST.com

Material
95 AU V142

blue

revision index

8

revision date

9/27/2019

page

3 / 3

No ASTM D2000 properties available

The given values are based on a limited number of tests on standard test pieces (2mm sheets) produced in the laboratory. The data from finished parts can deviate from above values depending on the manufacturing process and the component geometry.

The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisions do not plan for something else.

Freudenberg

Freudenberg FST GmbH
Global Material Technology
Wolfgang Becker

Telefon: +49 (0)6201/80-2893

Fax: +49 (0)6201/88-2893

Email: wolfgang.becker@FST.com